





CUPA 2

*Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with thin laminations and a **smooth surface**.*



 Riodolas mina, Carballeda de Valdeorras (Ourense) Spain.

 Operating since 1972.

 Sizes: 20x20 - 60x45 cm
Thickness: 3.5 - 5 - 6 mm




Formats



Rectangular Square Half Moon Waben Schuppen Fishschuppen 90° Sawn

Selections



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code: W1 (< 0,6%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 50 MPA	S1	T1	Fullfil < 0,6%

International certifications



European Standard: EN 12326 | French Specifications: NF44/03 - N°33235 | Belgian Specifications: ATG/H652 | British Standard: BS 680 Part 2